



产品说明书

Technical Datasheet

2018 版

材料类型 Material Type	PPA+GF45	牌号 Grade Name	PPA X6T 2345-HS
材料特性 Features	<ul style="list-style-type: none"> •热稳定性 Heat stability •高刚性 High stiffness •尺寸稳定性好 Good dimensional stability •成型加工性能好 Good molding and processing performance 		
材料标准 Material Standard			
供货地区 Availability	亚太	Asian-Pacific	
加工方法 Process Method	注射成型	Injection Molding	
外观 Appearance	颜色可选	Colors Optional	
用途 Applications	汽车, 电子电气	Automobile, Electrical/Electronic Applications	

通用性能 General Properties

序号 No.	性能 Properties	检验方法 Methods	单位 Units	典型值 Values	测试条件 Test Conditions
1	密度 Density	ISO 1183-1	g/cm ³	1.62	23℃
2	收缩率 Flow Molding shrinkage	PRET Method	%	0.2	23℃/48h
3	收缩率 Transverse Molding shrinkage	PRET Method	%	0.7	23℃/48h
4	拉伸强度 Tensile Strength at Max Load	ISO 527-2	MPa	200	50mm/min
5	断裂伸长率 Elongation at Break	ISO 527-2	%	1.0~2.5	50mm/min
6	弯曲强度 Flexural Strength	ISO 178	MPa	290	2mm/min
7	弯曲模量 Flexural Modulus	ISO 178	MPa	16000	2mm/min
8	冲击强度 Impact Strength	ISO 179-1	kJ/m ²	55	23℃
9	缺口冲击强度 Notched Impact Strength	ISO 179-1	kJ/m ²	9	23℃

加工参数 Processing conditions

干燥条件	Drying Cond.	110~125℃ *6~12h
含水率控制	Moisture Control	≤0.2%
注塑温度	Injection Temp.	300-335℃
模温	Mold Temp.	60~150℃

注: 以上数据为实验典型值, 真实可靠, 仅作参考, 不能认定为材料性能最小值。

Note: The technical data above are authentic and reliable for reference. These value cannot be defined as the minimal performance value.